

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 25/00, 2/08, 2/10	A1	(11) International Publication Number: WO 99/62570 (43) International Publication Date: 9 December 1999 (09.12.99)
(21) International Application Number: PCT/SE99/00896 (22) International Filing Date: 27 May 1999 (27.05.99) (30) Priority Data: 9801901-1 29 May 1998 (29.05.98) SE (71) Applicant (for all designated States except US): BONE SUPPORT AB [SE/SE]; Forskaregatan 1, S-275 37 Sjöbo (SE). (72) Inventor; and (75) Inventor/Applicant (for US only): LIDGREN, Lars, Åke, Alvar [SE/SE]; Örnvågen 35, S-227 31 Lund (SE). (74) Agents: WAGNER, Heinz et al.; H. Wagner & Co. AB, Norra Vallgatan 72, S-211 22 Malmö (SE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DE (Utility model), DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i> <i>In English translation (filed in Swedish).</i>
(54) Title: METHOD FOR MANUFACTURING A POWDER COMPONENT FOR CEMENT FOR MEDICAL USE, USE OF SUCH POWDER COMPONENT AND SUCH POWDER COMPONENT		
(57) Abstract A method for manufacturing the powder component for a cement for medical use is intended. The cement includes a liquid component containing a polymerizable substance and a powder component containing a plastic substance and an X-ray contrast medium. The liquid component and the powder component are adapted to be mixed for providing a setting mass which is set to form the cement. In order to prevent the formed cement from releasing particles wearing on articulating or bearing surfaces adjacent the point of cementation, a water soluble, non-ionic X-ray contrast medium is mixed with the plastic substance, and for minimizing the risk of damaging the powder component during the sterilisation, sterilising by radiation of the powder component containing said X-ray contrast medium is carried through at a negative pressure and/or in an inert gas atmosphere. Use of the powder component manufactured according to the above in a bone cement is also intended, as is the powder component itself.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

1.

Method for manufacturing a powder component for cement for medical use, use of such powder component and such powder component.

Aseptic loosening is the main longterm complication after a total joint replacement. The osteolysis seen in loosening is caused by, in combination, an increased fluid pressure and an increased inflammatory response to particles, preferably particles of high density polyethylene (HDPE). Another contributing main factor to loosening is related to the prosthetic stability within bone cement or between the cement and bone tissue.

Contrast agents such as barium sulphate (BaSO_4) and zirconium dioxide (ZrO_2) have been added to cement for medical use to achieve radiographic visibility, i.e. visibility to radiophotography, in order to check the operation result.

In order to improve the interface of cement for medical use, various substances such as e.g. hydroxyapatite and growth factors have been added to the cement. Hydroxyapatite has, inter alia, been used in compositions intended for reduction of the wear caused by fragmentation of the cement, whereby particles of the cement enter the joint cavity, i.e. the implant articulation.

There are today clear evidence of that agents impermeable to X-ray emission, i.e. radio opaque agents, which are harder than the metallic counterpart, may cause damages to the articulating surfaces, whereby the wear of the polyethylene increases markedly. In the vast majority of total joint replacement, one of the articulating or bearing surfaces consists namely of a hard, very smooth metallic or ceramic surface, while the other bearing surface is manufactured from high-molecular weight polyethylene. This polyethylene is used as a concave bearing surface. It has been shown that if the radiographic or X-ray contrast media are removed from the bone cement, wear will be reduced. Thus, it is of utmost importance

2.

either to abandon said X-ray contrast media, which is disliked by most surgeons, or to find an X-ray contrast medium which will not affect the strength to a greater extent than in existing cements for medical use, but
5 will be less abrasive when fragmented (released) from the cement.

This is possible by using new types of X-ray contrast media, so called non-ionic contrast media. Radiographic or X-ray contrast media of different types with
10 high osmolality and low osmolality are known today. These contrast media have a high affinity for absorbing water and are in fact water soluble. Preliminary experiments regarding the possibility of mixing these X-ray contrast media into bone cement have been carried through in a
15 laboratory and shows that this is possible and that good radiographic visibility, or visibility to radiophotography, is achieved. Studies are also carried through with bone cell cultures in order to study local toxicity. Existing studies show that non-ionic X-ray contrast media,
20 without being added to bone cement, have very low toxicity especially when contrast media having low osmolality are used.

The sterilisation procedure is of utmost importance for the production of a new cement for medical use. With
25 the non-ionic, water soluble, radiography or X-ray contrast medium, gas sterilisation will induce formation of lumps in the bone cement and sterilisation by radiation will be necessary. There is however, a clear influence by the sterilisation upon a range of cement properties
30 The tensile strength decreases in proportion to the dosage of gamma and beta radiation for the sterilisation. The fatigue resistance will also be significantly reduced. Rheology measurements show a large decrease in viscosity and a delay of the setting time after radiation. This
35 effect on acrylic cement by oxidative degradation has been shown to occur also in other polymers, or plastic substances, such a HDPE. If radiation is carried through

3.

in air, this will cause extensive oxidation and property deterioration in HDPE. This effect increases with time due to ageing of the material. It has been shown that if radiation is carried through at a negative pressure and/
5 /or by means of a protective inert gas, the dominant effect of the radiation will be cross-linking, not degradation. The effect is further improved if the plastic product after sterilisation by radiation is subjected to a heat treatment in an environment free of oxygen. Steri-
10 lisation at a negative pressure and at low temperature also provide improved properties to the polymer.

The object of the present invention is consequently to provide a method for manufacturing the powder component for a cement for medical use in order to prevent
15 the cement obtained from releasing particles which contribute to the wear of articulating or bearing surfaces adjacent the point of cementation as well as minimize the risk of damaging the powder component during sterilisation thereof.

20 This is arrived at according to the invention by the combination that a water soluble non-ionic X-ray contrast medium is mixed with the plastic substance, whereby particles of the X-ray contrast medium released from the cement after the cementation are dissolved and do not
25 thereby contribute to the wear of articulating or bearing surfaces adjacent the point of cementation, and that sterilisation by radiation of the powder component containing said X-ray contrast medium is carried through at a negative pressure and/or in an inert gas atmosphere in
30 order to minimize the risk of damaging the powder component during the sterilization thereof. The invention also include eventual heat treatment of the powder mixture in the oxygen-free atmosphere after the radiation treatment.

35 The object of the present invention is also to render it possible to use the powder component manufactured by said method in a cement which is used as bone cement.

4.

A further object of the invention is to provide a powder component which is manufactured in accordance with the abovementioned method.

Below, a method of manufacturing the powder component for a cement for medical use is described. Said cement includes a liquid component containing a polymerisable substance and a powder component containing a plastic substance and an X-ray contrast medium. The liquid and powder components are adapted to be mixed and thereby provide a setting mass which is set to form the cement. A water soluble, non-ionic X-ray contrast medium is mixed with the plastic substance, whereby particles of the X-ray contrast medium released from the cement after cementation are dissolved and do not thereby contribute to the wear of articulating or bearing surfaces adjacent the point of cementation.

Sterilisation by radiation of the powder component containing said X-ray contrast medium is carried through at a negative pressure and/or in an inert gas atmosphere for minimizing the risk of damaging the powder component during the sterilisation.

The water soluble non-ionic X-ray contrast medium which is mixed into the powder component is chosen preferably from the group consisting of iohexol, ioversol, iopamidol, iotrolane and iodixanol and has preferably low osmolality. Other X-ray contrast media which can be used are metrizamide, iodecimol, ioglucol, ioglucamide, ioglunide, iogulamide, iomeprol, iopentol, iopromide, iosarcol, iosimide, iotasul, ioxilane, iofratol and iodecol. Mixtures of said media can also be used.

In the following seven examples, various methods for producing said powder components are described:

Example 1

A non-ionic crystalline contrast medium, e.g. iohexol, is ground to a powder with a particle diameter of about 5 μm . The powder is then mixed with the plastic substance (polymer) in the powder component to an acrylic cement

5.

for medical use, e.g. bone cement, consisting of acrylic polymer particles, preferably polymethylmethacrylate and/or copolymers containing polymethylmethacrylate, with a particle size around 80-100 μm and a very small amount (about 0,5 percent by weight) of a so called initiator substance, e.g. benzoyl peroxide. The X-ray contrast medium comprises preferably about 17-23 percent by weight of the finished powder component (2-3 parts of contrast medium are mixed with 10 parts of the polymer).

Other additives can also be added to said powder component. The powder component is then packed up in bag-type portion packs or solid plastic containers, which in both cases are sealed with an air-permeable material, e.g. paper or plastic. The portion packs are placed one by one or in pairs in a further air-permeable bag or container which shall serve as a sterile barrier after sterilisation. Prior to sterilisation, these packs are placed in an air-proof container, the air is removed such that a negative pressure is generated, corresponding to an air pressure of 5 %, preferably about 2,5 %, of the atmospheric pressure. Furthermore, or as an alternative thereto, the container may be filled with an inert gas, e.g. argon, and sealed. The content of oxygen in the air-proof container should then be less than 1 %, preferably less than 0,5 %, of the atmospheric pressure, i.e. the amount of oxygen in the inert gas atmosphere corresponds to a partial pressure of 10 mbar at the most, preferably less than 5 mbar. Sterilisation of the powder component is now carried through by radiation, preferably beta or gamma radiation, with a dose of between 0,5 and 7 Mrad, preferably about 2,5 Mrad. After the sterilisation by radiation and at said negative pressure/inert gas atmosphere, the powder component may preferably be heated to a temperature of 50 - 120°C for 1 min. - 24 hours. After the sterilisation by radiation, the powder bags should preferably, but not necessarily, be kept in the oxygen-free atmosphere until the cement shall be used.

6.

Example 2

As example 1, but where the amount of contrast medium in the powder component is within a range determined by a weight ratio between the contrast medium and polymer of 0,08 : 1 to 0,6 : 1 or such that the powder component contains between about 5 and about 40 percent by weight of X-ray contrast medium.

Example 3

As examples 1-2, but the particle diameter of the non-ionic contrast medium is within a range of 1-50 μm and of the acrylic polymer particles within a range of 20 - 200 μm , with the limitation however, that the diameter of the polymer particles is at least four times the diameter of the contrast medium particles.

15 Example 4

As examples 1-3, where a powder of an antibiotic substance is added to the powder component before the sterilisation.

Example 5

20 As examples 1-4 with addition of a colouring substance, e.g. chlorophyll, to the powder component.

Example 6

As examples 1-5, but where the powder component is heated to about 80°C for one hour after the sterilisation by radiation, still packed in an oxygen-free environment.

Example 7

As examples 1-5 except that the powder component is packed directly in a cement mixing container, sealed by means of an air-permeable diaphragm. The cement mixing container filled with powder is packed in an air-permeable pack serving as a sterile barrier. This pack is then placed in an air-proof container, from which the oxygen in the air is evacuated, and sterilisation as in example 1 is carried through.

35 The powder component manufactured according to the above methods may suitably be used in a bone cement for

7.

fixing prostheses or parts of prostheses, but may also be used in cements for other medical purposes.

The powder components produced in accordance with the above examples thus contains a non-ionic X-ray contrast medium and it is sterilised at a negative pressure and/or in an inert gas atmosphere.

In the above methods, the inert gas atmosphere may, except for argon, consist of helium, neon or nitrogen or mixtures thereof.

8.

Claims:

1. Method for manufacturing the powder component for a cement for medical use,

said cement including a liquid component containing a polymerizable substance and a powder component containing a plastic substance and an X-ray contrast medium,
5 and

wherein the liquid component and the powder component are adapted to be mixed for providing a setting mass which is set to form the cement,

10 c h a r a c t e r i z e d b y
mixing a water soluble, non-ionic X-ray contrast medium with the plastic substance, whereby particles of said X-ray contrast medium released from the cement after cementation are dissolved and do not thereby contribute
15 to the wear of articulating or bearing surfaces adjacent the point of cementation, and

sterilising by radiation the powder component containing said X-ray contrast medium at a negative pressure and/or in an inert gas atmosphere for minimizing the risk
20 of damaging the powder component during the sterilisation.

2. Method according to claim 1, c h a r a c t e r i z e d b y selecting the water soluble, non-ionic X-ray contrast medium mixed into the powder component from the group consisting of iohexol, ioversol, iopamidol,
25 iotrolane, iodixanol, metrizamide, iodecimol, ioglucol, ioglucamide, ioglunide, iogulamide, iomeprol, iopentol, iopromide, iosarcol, iosimide, iotasul, ioxilane, iofrattol and iodecol or mixtures thereof.

3. Method according to claim 1 or 2, c h a r a c t e r i z e d b y the water soluble, non-ionic X-ray contrast medium having low osmolality.
30

4. Method according to any of claims 1-3, c h a r a c t e r i z e d b y bringing the powder component to contain maximum 40 % by weight of water soluble, non-
35 -ionic X-ray contrast medium.

9.

5. Method according to claim 4, c h a r a c t e -
r i z e d b y bringing the powder component to con-
tain between 5 and 40 % by weight of water soluble, non-
-ionic X-ray contrast medium.

5 6. Method according to claim 4 or 5, c h a r a c -
t e r i z e d b y bringing the powder component to
contain between 17 and 23 % by weight of water soluble,
non-ionic X-ray contrast medium.

7. Method according to any of claims 1-6, c h a -
10 r a c t e r i z e d b y bringing the water soluble,
non-ionic X-ray contrast medium to have a particle dia-
meter of maximum 25 % of the particle diameter of the
plastic substance.

8. Method according to claim 7, c h a r a c t e -
15 r i z e d b y bringing the water soluble, non-ionic
X-ray contrast medium to have a particle diameter of be-
tween 1 and 50 μm , while the particle diameter of the
plastic substance is between 20 and 200 μm .

9. Method according to claim 7 or 8, c h a r a c -
20 t e r i z e d b y bringing the water soluble, non-ionic
X-ray contrast medium to have a particle diameter of about
5 μm , while the particle diameter of the plastic substance
is between 80 and 100 μm .

10. Method according to any of claims 1-9, c h a -
25 r a c t e r i z e d b y carrying through the sterili-
sation by radiation by means of beta or gamma radiation
and with a radiation dose of between 0,5 and 7 Mrad.

11. Method according to any of claims 1-10, c h a -
r a c t e r i z e d b y carrying through the sterilisa-
30 tion by radiation at a negative pressure corresponding
to an absolute air pressure of 5 % at the most, prefer-
ably about 2,5 %, of the atmospheric pressure.

12. Method according to any of claims 1-11, c h a -
r a c t e r i z e d b y carrying through the sterilisa-
35 tion by radiation at a negative pressure and at low tem-
perature, preferably about 77°K.

13. Method according to any of claims 1-12, c h a -

10.

r a c t e r i z e d b y carrying through the sterilisation by radiation in an inert gas atmosphere, said inert gas atmosphere consisting of argon, helium, neon or nitrogen.

- 5 14. Method according to any of claims 1-13, c h a -
r a c t e r i z e d b y carrying through the sterilisation by radiation in an inert gas atmosphere in which the amount of oxygen corresponds to a partial pressure of 10 mbar at the most, preferably less than 5 mbar.
- 10 15. Method according to any of claims 1-14, c h a -
r a c t e r i z e d b y heating the powder component to 50 - 120°C for 1 min. - 24 hours after sterilisation by radiation and at a negative pressure and/or an inert atmosphere.
- 15 16. Method according to any of claims 1-15, c h a -
r a c t e r i z e d b y selecting as plastic substance in the powder component acrylic polymer particles, preferably polymethylmethacrylate and/or copolymers containing polymethylmethacrylate.
- 20 17. Method according to any of claims 1-16, c h a -
r a c t e r i z e d b y adding a substance initiating polymerization, e.g. benzoyl peroxide, to the powder component before the sterilisation by radiation.
18. Method according to any of claims 1-17, c h a -
25 r a c t e r i z e d b y adding an antibiotic substance to the powder component before the sterilisation by radiation.
19. Method according to any of claims 1-18, c h a -
r a c t e r i z e d b y adding a coburing substance,
30 e.g. chlorophyll, to the powder component before the sterilisation by radiation.
20. Method according to any of claims 1-19,
c h a r a c t e r i z e d b y
 placing the powder component in an air-permeable con-
35 tainer,
 placing in turn the air-permeable container in an air-proof container,

11.

evacuating air from the air-proof container, and
sterilising by radiation the powder component in the
air-permeable container.

21. Method according to claim 20, c h a r a c t e -
5 r i z e d b y locating the powder component in a bone
cement mixing container.

22. Use of a powder component obtained by the method
according to any of claims 1-21 in a bone cement for
fixing prostheses or parts of prostheses.

10 23. Powder component for cement for medical use,
c h a r a c t e r i z e d i n
that it contains a water soluble, non-ionic X-ray
contrast medium, and

15 that it is sterilised at a negative pressure and/or
in an inert gas atmosphere.

24. Powder component according to claim 23, c h a -
r a c t e r i z e d i n that the water soluble, non-
-ionic X-ray contrast medium which is mixed into the pow-
der component is selected from the group consisting of
20 iohexol, ioversol, iopamidol, iotrolane, iodixanol, met-
rizamide, iodecimol, ioglucol, ioglucamide, ioglunide,
iogulamide, iomeprol, iopentol, iopromide, iosarcol,
iosimide, iotasul, ioxilane, iofratol and iodecol or mix-
tures thereof.

25 25. Powder component according to claim 23 or 24,
c h a r a c t e r i z e d i n that it contains maxi-
mum 40 % by weight of water soluble, non-ionic X-ray
contrast medium.

26. Powder component according to any of claims 23-25,
30 c h a r a c t e r i z e d i n that it contains between
5 and 40 % by weight of water soluble, non-ionic X-ray
contrast medium.

27. Powder component according to any of claims 23-26,
c h a r a c t e r i z e d i n that the powder compo-
35 nent contains between 17 and 23 % by weight of water so-
luble, non-ionic X-ray contrast medium.

28. Powder component according to any of claims 23-27,

12.

c h a r a c t e r i z e d i n that the water soluble, non-ionic X-ray contrast medium has a particle diameter of maximum 25 % of the particle diameter of the plastic substance.

5 29. Powder component according to any of claims 23-28, c h a r a c t e r i z e d i n that the water soluble, non-ionic X-ray contrast medium has a particle diameter of between 1 and 50 μm , while the particle diameter of the plastic substance is between 20 and 200 μm .

10 30. Powder component according to any of claims 23-29, c h a r a c t e r i z e d i n that the water soluble, non-ionic X-ray contrast medium has a particle diameter of about 5 μm , while the particle diameter of the plastic substance is between 80 and 100 μm .

15 31. Powder component according to any of claims 23-30, c h a r a c t e r i z e d i n that it contains an anti-biotic substance.

20 32. Powder component according to any of claims 23-31, c h a r a c t e r i z e d i n that it contains a cobu-ring substance, e.g. chlorophyll.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 99/00896

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: A61L 25/00, A61L 2/08, A61L 2/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0639382 A1 (MIT PHARMACA AB), 22 February 1995 (22.02.95) --	1-32
A	EP 0676212 A1 (BRISTOL-MYERS SQUIBB COMPANY), 11 October 1995 (11.10.95) --	1-32
A	EP 0701824 A2 (MERCK PATENT GMBH), 20 March 1996 (20.03.96) --	1-32
A	EP 0705609 A2 (MERCK PATENT GMBH), 10 April 1996 (10.04.96) -- -----	1-32

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

7 Sept. 1999

Date of mailing of the international search report

01-10-1999

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Eva Johansson/EÖ

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

02/08/99

International application No.

PCT/SE 99/00896

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0639382 A1	22/02/95	CA 2129910 A SE 510491 C SE 9302672 A	19/02/95 31/05/99 19/02/95
EP 0676212 A1	11/10/95	AU 684898 B AU 1615695 A CA 2145483 A CN 1114178 A JP 8038588 A US 5538514 A	08/01/98 19/10/95 08/10/95 03/01/96 13/02/96 23/07/96
EP 0701824 A2	20/03/96	AU 3053195 A CA 2158402 A CN 1126618 A CZ 9502390 A DE 4433201 A HU 75249 A HU 9502712 D JP 8103491 A NO 953651 A PL 310492 A SK 114495 A US 5797873 A ZA 9507807 A	04/04/96 18/03/96 17/07/96 17/04/96 21/03/96 28/05/97 00/00/00 23/04/96 18/03/96 18/03/96 03/04/96 25/08/98 07/05/96
EP 0705609 A2	10/04/96	AU 3300595 A BR 9504293 A CA 2159871 A CN 1127700 A CZ 9502574 A DE 4435680 A JP 8117322 A PL 310793 A US 5650108 A ZA 9508407 A	18/04/96 01/10/96 07/04/96 31/07/96 17/04/96 11/04/96 14/05/96 15/04/96 22/07/97 08/05/96